

PRODUCT DATA SHEET

SikaPlast®-115

Mid-Range Water Reducing/Plasticising Concrete Admixture

PRODUCT DESCRIPTION

SikaPlast®-115 is a liquid admixture for concrete which is used as a mid-range water reducer/plasticiser. It meets the requirement of BS EN 934 -2.

USES

- SikaPlast®-115 is suitable for the production of ready mixed concrete
- Applications that require high quality concrete
- Applications that require improved consistence retention
- Utilisation of crushed rock fines in concrete

CHARACTERISTICS / ADVANTAGES

- Mid-range water reductions resulting in higher strengths and densities
- Flexible application as both WRA and HRWR
- Less sensitive to variations in cement and aggregate types
- Improved cohesion properties

- Improved early and ultimate strengths
- Improved rheology
- Improved durability
- Reduced segregation and bleeding
- Reduced drying shrinkage
- Reduced mix costs
- * Compared to concrete without admixture

APPROVALS / STANDARDS

Conforms to the requirements of BS EN 934-2 Table 2 DoP 79475100, certified by Factory Production Control Body 1029 and provided with the CE mark DoC 66487744, certified by Factory Production Control Body 0120 and provided with the UKCA mark

PRODUCT INFORMATION

Chemical Base	Modified polycarboxylate blend
Packaging	20 litre drum, 1000 litre IBC
Shelf Life	12 months from date of production if stored properly in undamaged containers.
Storage Conditions	Store in dry conditions at temperatures between +5°C and +25°C. Protect from direct sunlight and frost.
Appearance / Colour	Brown liquid
Specific gravity	1.11 kg/L (at +20°C)
Total Chloride Ion Content	<0.1 % (chloride free)
Equivalent Sodium Oxide	<0.40 % (alkali content)
Equivalent Sodium Oxide	<0.40 % (alkali content)

Product Data Sheet

SikaPlast®-115November 2022, Version 01.02
021301011000004287

TECHNICAL INFORMATION

Specific Advice	Effect on Setting: Slight extension to normal setting Effect of Overdosing: Increased workability and segregation
	SikaPlast®-115 should not be added to dry cement
	SikaPlast®-115 should be added with the mixing water
	Support from our Technical Service Department is recommended

APPLICATION INFORMATION

Recommended Dosage	0.3 - 1.2 % by weight of cement
Dispensing	SikaPlast®-115 should be dispensed through suitable calibrated dosing equipment.
Compatibility	Sika Admixtures: Compatibility information available on request Cements: All cement combination

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

Application Method / Tools

- The standard rules of good concreting practice, concerning production as well as placing, are to be followed. Refer to relevant standards. Fresh concrete must be cured properly.
- SikaPlast®-115 should not be added to dry cement
- SikaPlast®-115 should be added with the mixing water

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

SIKA LIMITED

MEGAL NOTES

Welwyn Garden City

The finition and in particular, the recommendations relating to the application and end-use of Sika web www.sika.co.uk products, are given in good faith based on Sika's current knowledge and experience of the products when







Product Data Sheet SikaPlast®-115

November 2022, Version 01.02 021301011000004287

properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaPlast-115-en-GB-(11-2022)-1-2.pdf

